



Abatement by Encasement:
Safeguarding People while Saving MoneySM.

ENCASUREMENT GUIDELINE FOR PAINTED SURFACES

INTRODUCTION

The encasement system consisting of SE-110 Penetrating-Stabilizer (primer) and SE-120 or SE-130 Protective Skin (topcoats) have been extensively ASTM tested and found to meet the EPA's requirements for a 20-year encapsulant when applied over Lead-Based Paint at a minimum application rate of 10 wet mils of each product. Little or no surface preparation is required in most cases other than to remove the very loose, flaking paint. This protective coating system has also been used extensively when lead-free paints are involved because of the substantial savings in surface preparation labor that can be achieved. When dealing with metal surfaces, the use of SE-110-CI corrosion-inhibiting primer is recommended to minimize or eliminate the usual preparation required to remove rust (refer to Specification No. 01-2 for further information on dealing with metal surfaces). When dealing with painted masonry walls, it is often necessary to pressure wash the surface to remove efflorescence, which also removes any very loose, flaking paint.

SURFACE EVALUATION

The suitability of a surface for the application of Safe Encasement's two-coat system can, at times, be determined by visual inspection by experienced applicators. It is required in MA and CT and always recommended elsewhere that test patches be used to evaluate whether or not adequate adhesion is achieved without any removal of loose, flaking paint. After the test patches have fully cured, the adhesion is determined by using an "X-cut" test method. In some cases, e.g. where large areas of intact paint are present (free of cracks, peeling, flaking, etc.), an "X-cut" test should be performed on the existing paint to determine if there are adhesion problems between the existing paint and the substrate and between layers of the old paint. This could indicate that a portion of the surface is not a good candidate for encasement. Allow test patches to dry thoroughly before testing for adhesion or other properties (14-30 days).

APPLICATION

Both the primer and topcoats are water-based, acrylic elastomers that can be applied by spraying, brushing or rolling. The SE-110 (and SE-110-CI) primers are milky as applied, but dry to a clear tacky film. The primer can be over-coated once the film is no longer milky in color, even though it may not be fully dry at that point in time. The system is usually dry enough within a few hours to over night that the area can be re-occupied. However, complete drying to full physical properties usually requires 7-14 days, with poor drying conditions (low temperatures and/or high humidity) can extend this drying time. No physical testing such as "X-cut" tests should be carried out until the system is completely dry. Please refer to Technical Bulletin No. 01-2 for more information on curing/drying. As regards spraying, any commercial airless sprayer (minimum 1 GPM rated) capable of developing up to 3,000 PSI can be used. The choice of spray tip depends on the job. Typically, any tip size from 0.017 to 0.025 inches will work well, with the width of the spray

SAFE Encasement Systems ~ 7860 Dana Point Ct. ~ Las Vegas, NV 89117-1927

Phone: (888) 277-8834 or (702) 360-6111 ~ Fax: (888) 277-8835 or (702) 360-5827

www.safeencasement.com



Abatement by Encasement:
Safeguarding People while Saving MoneySM.

Page 2 of 2

pattern being dictated by the surface to be covered. Experience has shown that it is best to spray water through the sprayer first for several minutes. Then turn the sprayer off and transfer the feed tube to the pail of coating materials. Turn the sprayer back on and spray into another pail until full strength product begins to discharge from the nozzle. You are then ready to apply encasement materials. Cleanup is with water. Generous amounts of water should be used to flush all spraying equipment to prevent buildup in the equipment. Before using, the coating should be stirred with a power stirrer to insure the contents of the pail are uniformly mixed.

REPAIRS WITH SES SEALANTS (CAULK)

If the encased surface is rougher than desired due to the presence of surface imperfections (holes, cracks, thick flakes, etc.), SE-150 (trowel-able grade) or SE-151 sealant (in tubes) can be applied and spread with a blade to fill in holes, valleys, etc. after priming but prior to the application of the topcoat. The caulk should be allowed to dry until the surface is dry and firm to the touch.

COVERAGES

As regards the matter of insuring that sufficient coverage is achieved, a wet film thickness gauge should be used to check the thickness of the freshly applied materials. A second way to check on the average coverage rate is to keep track of the rate of consumption and square feet of surface covered, e.g. at 10 wet mils the coverage rate is 150 sq. ft./gallon on a flat surface, or approximately 750-800 sq. ft. per 5 gallon pail. An experienced applicator will often be able to tell from the appearance (sheen) of the freshly coated surface if sufficient coating material is being applied as where the thickness was measured.

CAUTION

The products should not be applied when it is possible for the temperature to fall below 32°F within 10-14 days following the application. Freezing of any water remaining in the coating next to the substrate surface will destroy the bond between the newly applied coating system and the surface. Because this encasement coating system is quite a bit thicker than conventional paints, it takes much longer to dry/cure fully.

FURTHER INFORMATION

For further information or answers to questions, please contact Safe Encasement Systems at the number below or your nearest sales representative or distributor.

File name: Encasement Guide for Painted Surfaces (06-04) – Specification No. 01-1

SAFE Encasement Systems ~ 7860 Dana Point Ct. ~ Las Vegas, NV 89117-1927

Phone: (888) 277-8834 or (702) 360-6111 ~ Fax: (888) 277-8835 or (702) 360-5827

www.safeencasement.com